Dean&Francis

ISSN 2959-6157

Balancing Remarkable Properties and Commercial Challenges: To What Extent Can Graphene Revolutionize Future Technologies?

Zihao Shen

Abstract:

The current dissertation focuses on the question of whether the exceptional electrical and mechanical properties of graphene can lend themselves to transformative applications occurring at scale or only serve special applications. The extreme reliance on graphene instead of the larger category of two-dimensional materials allowed comparison of the electron mobility (~200,000 cm 2 / V s) and tensile strength (~130 GPa) of graphene with current material technologies (silicon, copper, and steel). In a systematic literature review of peer-reviewed Q1/Q2 journals, industry reports, and conference results selected with discretion, I compared the potential of graphene as applied to analogue electronics with the fact that it has zero band gap, its mechanical robustness in the laboratory with the issues of preventing defects and integrating composites. A major cost analysis showed that production of existing CVD-derived monolayer graphene was so expensive ($1000 to 5000/g) that it would only be considered as a specialty product until roll-to-roll and exfoliation processes were developed. The potential of quantum computing, construction composites, and policy-driven commercialization was analyzed and weighed against the success of earlier pilot efforts in light of scale, dispersion, and regulatory challenges. The reflective review identifies delays in the scope refinements, publication delays, and a lack of interpretive opportunities in the socio-economic dimensions, and suggests more concerted initial scope, a living log of research alerts, and time-blocking in future projects. The results indicate that graphene has the potential to transform certain high-value industries indeed, but that its more general industrial influence remains dependent upon the successful resolution of basic materials-engineering, manufacturing, and policy issues.

Keywords: : Graphene; Material Properties; Commercialization; Two-Dimensional Materials; Technological Applications

ISSN 2959-6157

1. Introduction

Graphene is considered a wonder material of the 21st century, having been isolated in 2004 by Andre Geim and Konstantin Novoselov at the University of Manchester (Novoselov et al., 2004). Its findings had won over the researchers the Nobel Prize in Physics in 2010 and had sparked a wave of research worldwide about what it could do. Graphene is known to be arranged in a two-dimensional honeycomb lattice of two-dimension with one layer of carbon atoms. It forms an unusual composition with excellent characteristics, such as its mechanical strength is 200 times higher than steel, its thermal conductivity is ~5000 W/m K, and its electron mobility is extremely high with a value of >200,000 cm 2/V. s (Li et al., 2024).

The numerous applications in which graphene can offer multiple benefits include next-generation transistors, medical diagnostics, supercapacitors, and desalination membranes (Yusaf et al., 2022; Saeed et al., 2025). With the search for industries for more efficient and sustainable substitutes for the present-day materials, graphene is proposed as a solution. Some obstacles like manufacturing expenses, environmental system changes over nanoparticle toxicity, and the absence of massive manufacturing infrastructure still limit the commercialization process (Dhall et al., 2024).

In the present dissertation, the researcher will set out to examine how intrinsic properties of graphene have the potential to change current contemporary technologies, not only examining its transformational capabilities but also identifying the challenges that need to be addressed. The paper takes a critical stance to review whether or not graphene can move beyond a laboratory novelty to a commercially viable industrial substance, utilizing secondary data derived from scholarly journals, institutional publications, and market reports. In the process, it will also draw parallels between graphene and conventional surfaces such as silicon, copper, and steel to illustrate its strengths and weaknesses.

2. Literature Review

2.1 Background of Graphene

2.1.1 Discovery and Development

The isolation breakthrough of graphene took place in the year 2004, when Professors Andre Geim and Konstantin Novoselov discovered an immensely easy technique referred to as mechanical exfoliation. It was accomplished by means of removing successive layers of graphite with the help of adhesive tape until one monolayer of carbon atoms was created (Zhang et al., 2021). Before this discovery, two-dimensional (2D) materials such as graphene were confirmed to be mathematically possible, and some argued that they could never exist as individual entities because they are thermodynamically unstable. This breakthrough not only indicates that it was possible to obtain a free-standing form of graphene but also introduces the world to its amazing properties, prompting scientific interest in the material to spread like wildfire around the world. The discovery became important and was adapted in 2010 with a Nobel Prize in Physics. Given that graphene is the most promising discovery so far, efforts to explore its potential have gone beyond the laboratory into vast-scale, collaborative projects between several universities, university research institutions, and government launched funded programs. One example of a larger project is the Graphene Flagship project, started by the European Union in 2013, with an initial budget of 1 billion euros (Sama, 2024). The program is designed to address the research and commercialization gap, and its strategy is to ensure a faster integration of technologies and applications of graphene into other sectors. A history of carbon-based materials starting with nanodiamonds in 1963, fullerenes in 1985, multi-wall carbon nanotubes in 1991, single-wall carbon nanotubes in 1993, carbon nanohorns in 1999, graphene in 2004, graphene quantum dots in 2010, and carbon dots in a recent undated year highlights the gradual development of carbon nanomaterials resulting in the prominent presence of graphene.



Figure 1: Timeline of Discovered Graphene

As an increasingly popular substance, approaches to the production of graphene have proliferated considerably. Mechanical exfoliation is considered a perfect way to produce high-purity graphene, but it does not apply on a large scale. As measures of alleviating this, various other methods have been formulated to synthesize:

· Chemical Vapor Diffusion (CVD): The most common method to produce graphene on a large scale (especially in copper) CVD process is easily controllable in layer thickness and area. It is, however, constrained by the existence of grain boundaries and defects (Cheng et al., 2021).

· Liquid-phase exfoliation: It utilizes grafting graphene in a solvent by sonication in order to manufacture large quantities. The product graphene, however, is lower in quality as compared to CVD or mechanical exfoliation (Hernandez et al., 2008).

· Epitaxial growth: Sublimation of silicon atoms produced by heating silicon carbide causes a carbon-enriched layer to form and reform into graphene. It is a good quality alternative to this technique, but it is complicated and less scalable (Emtsev et al., 2009).

2.1.2 Structural Properties

The unconventional characteristics of graphene are attributed to the Atomic structure. It is a single layer with carbon atoms organized to create a honeycomb lattice in two dimensions. All carbon atoms are linked with three others through the sp^2 hybridized orbitals, forming strong in-plane covalent bonds, but free π-electrons move on both sides of the plane (Szroeder et al., 2025). These π-electrons are behind most of the electronic and optical properties of graphene. The length of the C-C bond in graphene is about 0.142 nm, and the graph is also found to have an interlayer distance of 0.335 nm when the layers are superimposed (like graphite). Such an arrangement

ISSN 2959-6157

offers a very high surface area e.g. 2630 m2/g, in case of a single sheet of graphene, which is useful in specific cases like the development of sensors, supercapacitors, and judgement membranes used in water purification applications (Yang et al., 2018).



Figure 2: Structural View of Graphene

Due to the two-dimensional nature of graphene, its flare and optical transparency cannot be greater. It is almost transparent and average absorption of visible light is about 2.3% per layer (Li et al. 2019). It has played its part in its success as a transparent touchscreen, smart window and wearable electronic devices material. In particular, the structure of graphene results in the quasi-relativistic nature of the charge carriers which are in fact massless Dirac fermions. This Help make graphene has extraordinary electricity mobility and keep interested in-studying quantum Hall effects, spintronics, and several other exotic applications within the subject of physics (Avsar et al., 2020).

2.1.3 Electrical and Mechanical Properties

The most hailed of all the properties of graphene is its electrical conductivity. Graphene is a promising material that does not have a bandgap because there are low effective mass and allowing motion of electrons to move at high speed with negligible resistance. In optimal circumstances, its mobility at normal temperatures surpasses 200,000 cm 2 /V s even at room temperature, which is several orders of magnitude higher compared to the conventional semiconductors such as silicon (Rahman, 2014). Furthermore, it can be doped and/or challenged using an electric field to change its conductivity, so the material is a prospective component of field-effect transistors (FETs), photodetectors, and interconnects in ICs (Liang et al., 2024).



Figure 3: Summarized Properties of Graphene (Electrical, Mechanical, and Thermal)

Jalali et al. (2024) found that it is nearly 130 GPa and, as such, 100 or more times stronger than steel by weight. It has a Young modulus of about 1 TPa and is very bendable and stretchy to 20% of its original length without fracture, despite its toughness. The second important property is thermal conductivity, which is between ~5000 W/m K-more than two times higher than that of diamond, which used to be the record holder (Zhao et al., 2024). This renders graphene very suitable for high-performance computing systems as well as for thermal management of nanoelectronics.

2.2 Applications of Graphene

2.2.1 Graphene in Electronics

The use of graphene in the area of electronics is one of the most promising spheres that can be changed radically by the peculiarities of the substance. The unique electrical properties of graphene as the total number of electrons that can travel through it is huge, and its mobility is higher than 200,000 cm^2 / Vs / at room temperature, and the thickness of the material is atomic scale, which is a breakthrough compared to traditional materials (Ariga, 2022). The qualities make it a possible candidate to drive the current generation of electronic devices and particularly transistor which make the blocks of contemporary circuitry. The commonly used silicon-based transistors are pushing boundaries - the old standby to deliver technological change are reaching the physical and theoretical limits. Limitations on miniaturization, when it is getting harder and harder to reduce the size of the components further and the problem of cooling the component, the close density of the transistors developing heat, must be solved before the next step can be made.

ISSN 2959-6157



Figure 4: Graphene Electronic Market Size in USD Billion (2019-2032)

The two-dimensional structure of graphene and its unrivalled electron mobility offer an opportunity to move beyond these impediments to seek potentially the high speed-low power devices to revolutionize computing and communications. There is much development which have been done, in the practical utilization of graphene in electronics. Graphene field-effect transistor (GFETs) have already been successfully fabricated by the researchers and Krishnan et al. (2024) demonstrated the amazing switching speed at the terahertz (THz) regimes. Such high switching speeds mean that transistors composed of the material would lend themselves to high-speed data processing applications, including high-speed telecommunications and high-performance computing. The challenge, however, is another serious one: pure graphene does not have a bandgap, the energy separation that permits a material to behave effectively as a switch, turning off completely.

Methods including bilayer graphene stacking, where a bandgap can be introduced by placing two sheets of graphene in registry with each other, the interactions between a substrate and graphene changing the electronic properties of the graphene via the material interface, and the production of graphene nanoribbons, strips of graphene with engineered edge structure, are promising developments to improve the semiconducting properties of graphene. The flexibility and conductivity have made it a promising material in flexible electronics, bendable electronics, and wearable electronics, which are gaining demand in consumer electronics. The transparency and high electrical conductivity of graphene have made it the prime candidate as a transparent conductive electrode, which is an application of touchscreen devices, solar cells, and organic light-emitting diodes (OLEDs) (Miao and Fan, 2023).

High-frequency applications Graphene is being used to develop next-generation wireless communications systems; this is because radio-frequency (RF at high frequencies, graphene will be able to transfer information between devices at unprecedented speeds. Some of the key industry players are already spending a lot of money on this technology. Samsung has developed prototypes of graphene-based displays that will be characterized by improved resistance and brightness, whereas IBM has been working on graphene that will serve as communication components and that will enable improved efficiency in data transmission (Sengupta, and Hussain, 2024). The electronic market for graphene is very sturdy, as it is supported by growing demand and technological advancement. The industry has a growing market value, as projections point to the ballooning growth of the industry into the impressive USD 1596.1 billion by 2032, surpassing the current situation of USD 50.70 billion by 2024, with its compound annual growth rate (CAGR) rating it as of economic importance (MMR, 2025).

The type market segmentation shows a wide range of applications with graphene transistors projected as the highest with 204 Mn units (Mn), then followed by graphene supercapacitors, chips, and an integrated circuit (IC), sensors, and others in 2024. The Asia Pacific region owns the maximum market share in the year 2024, driven because of its strong manufacturing power and the adoption of technologies, especially in places such as China, South Korea, and Japan. North America follows, driven by significant research and development efforts and corporate investment, while Europe, the Middle East, and Africa, and South America contribute to the global distribution, as illustrated in the regional pie chart.

2.2.2 Biomedical Applications

The infinite surface area, the compatibility with life environments (when they are suitably functionalized), and the ability to readily modify the surface have placed graphene as an emerging material in the field of biomedical engineering. It is progressively researched as a drug delivery agent, a biosensor, an antibacterial coating, and a tissue engineer. Functionalized forms of graphene, in the form of graphene oxide (GO) in particular, have found the most success in drug delivery. Due to the large amount of oxygen-carrying active groups, it can conjugate with a number of drugs, and discharge them in a regulated fashion on exacting stimuli such as pH or temperature (Sonker et al., 2021). As an example, GO has been used about delivery anti-cancer drugs for instance DOXO (doxorubicin), which has high efficacy, to the tumors.



Figure 5: Biomedical Application of Graphene

The high conductivity and surface sensitivity of graphene, however, have also been harnessed to make graphene an ideal material in the detection of biomolecules such as glucose, DNA or pathogens down to ultralow levels in biosensing (Eivazzadeh et al., 2022). Such sensors have even found their way into wearable equipment fatigue, for instance; such equipment may well be able to monitor health, again in real-time. Besides, graphene and its derived compounds also attract the screening as neural interfaces and tissue regeneration scaffolds subject to the mechanical compliances and electrical properties for the improvement of cell differentiation and growth. The questions are focused on the fact that under certain circumstances in a cell, graphene may reactive oxidation species (ROS) and oxidize cell membranes. Consequently, biocompatibility impact testing is required to be completed as a zip preceding a clinical testing transaction.

2.3 Graphene in Energy Storage

Graphene has been one of the pillars of the energy stor-

ISSN 2959-6157

age and energy conversion technologies due to the high electrical conductivity and the ultrahigh surface area and unprecedented structural flexibility. The properties make it an elastic material in the development of lithium-ion batteries (LIBs), supercapacitor and fuel cells, etc Graphene is a key material with respect to theurra rate improvement of LIBs electrodes and the anode material and conductive additive. This form of integration has the potential to charge capacity radically and creates a circularity of stability and charging rate the greatest limitation in the conventional battery architecture. Graphene and silicon composites have presented new opportunities with much more gains in energy storage capacity than for the typical graphitic anode (Zhao et. al, 2024). Graphene-silicon composites have brought out more potential with way more advances in energy storage potential as compared to typical graphitic anode (Zhao et. al, 2024).

An energy storage system battery cell based on the use of graphene, the anode, cathode, separator, electrolyte and ion charge transport is optimized, the present collectors can contribute in efficient conduction. Essential elements such as lithium metal oxide, carbon electrodes, polymeric film, positive/negative electrodes have been designed and engineered to improve loading, performance, efficiency, electrochemical reaction capacity, voltage discharge, recharge and properly integrated with the grid system. It makes graphene a fundamental aspect in renewable and sustainable energy solutions and the innovator in engineering, science, research and development (Zhao et al, 2024).



Figure 6: Graphene Batteries

Graphene additionally offers this option to electric double layer capacitance, pseudo-capacitance itself for electric double layer capacitance in supercapacitors, especially as a blend with metal oxides or conductive polymers. The energy density of devices with graphene-based electrodes is currently even higher than 85 Wh/Kg and the power density well above 10kW/Kg - comparable and even superior to commercial capacitors (Kowsari, 2015). These breakthroughs have demonstrated the ability of graphene to transform the energy storage industry with ground breaking solutions to the performance incumbent energy storage technologies. Graphene improves the properties of proton exchange membrane (PEM) for hydrogen fuel in the aspect of increasing ionic conductivity and low durability. It is also capable to help with the catalyst dispersion in oxygen reduction reactions (ORR) that is key in energy conversion (Wang et al. 2014). The functions are significant in the implementations of cleaner systems of energy and more sustainable system of energy alongside with the international move at switching to renewable sources of energy and reduction of the carbon footprint.

2.4 Environmental Applications

Graphene has found some application in water purification in desalination and decontamination systems because of the high retention and selective permeability of graphene. The filter can take the form of a membrane of graphene oxide and has the ability to be selective and only allow the passage of molecules of water, however, any other possible contaminate, be it a heavy metal, a bacteria or salts. In 2017, researchers demonstrated that effective use of such membranes opens an opportunity to conduct desalination that widens possibilities of filtration of water on a larger scale. Graphene is being studied as a photocatalyst to purify air and degrade organic pollutants. Its integration into titanium dioxide (TiO_2) matrices furthers visible light absorption and the event of electron-hole separation, driving photocatalytic activity. Graphene foams and aerogels have found applications in the cleanup of oil spills, which exhibit high absorption capacities (more than 100 times their weight), and thermal treatment of these materials allows reuse.

3. Discussion

3.1 Comparing Graphene with Traditional Materials

The innovative characteristics of graphene have triggered scientists and business executives to consider graphene as a better alternative to conventional materials (silicon, copper, and steel, to name a few). In comparison of the electrical, mechanical, and economic properties of graphene and other existing materials in the market, this section compares whether graphene is a technological revolution or it is the marketing of the day.

3.1.1 Electrical Conductivity

The notoriety of graphene in the chemical material text is attributed to the runaway electrons conductivity. With crystalline, defect-free, and room temperature, then, millions of times greater than the silicon world record of 1,400 cm2/V s, graphene electrons have the potential to propagate even before crystallization, and in the absence of defects (Balandin, 2011; Castro Neto et al., 2009). Graphene has special properties because of its two-dimensional honeycomb structure of carbon atoms that are sp2-bonded and thus reduce scattering and allow electrons to travel virtually ballistically over a distance of less than a submicron. With device geometries already shrinking, graphene may be an unusually low resistance carrier of interconnects, with significantly lower resistive losses and vastly higher current densities than can be currently achieved by the current conventional copper conductor wiring (Schwierz, 2010).

Although it has these benefits, the zero bandgap of graphene presents an enormous limitation, which is that it cannot switch off the electron flow entirely. In digital electronics, logic operations simply require being able to switch between conductive (on) and insulating (off) states, a capability which the 1.1eV bandgap of silicon has proven to be very successful at, underpinning the complementary metal-oxide semiconductor (CMOS) technology. The bandgaps induced have been on the order of a few hundred millielectronvolts by efforts to induce a bandgap in graphene using lithographically-defined graphene nanoribbons, chemical functionalization, or an electric field applied to bilayer graphene. However, these methods currently have edge roughness, non-uniformity of doping concentration, or require complicated multiple-layer systems, none of which have developed into commercially deployable processes (Han et al., 2007).

The middle way has taken the form of so-called hybrid graphene-silicon architectures, in which, in principle, graphene is made to do what it can best do--analogue signal transmission or radio-frequency (RF) interconnects, say--and silicon is left to handle the stuff that matters in digital logic terms. Prototypical graphene-silicon heterostructures have been demonstrated to offer potentially useful amplifier behaviour at high frequencies, offering higher gain-bandwidth products than silicon-only (Castro Neto et al., 2009).

3.1.2 Mechanical Strength

Graphene boasts of mechanical properties that are said to be revolutionary: tensile strength of about 130 GPa, tens or hundreds of times better than high-grade steel, and a Young's modulus of about 1 TPa (Lee et al., 2008). Advocates think that this kind of power-to-weight ratio would break through the use of composites in the aerospace, defensive, and sports equipment industries, to allow lighter yet stronger structures that are stronger than the existing alloys. Besides, the two-dimensional elasticity of graphene, which can be stretched up to ~20 % before rupture, enables the possibility of highly flexible electronics, soft robotics, and even artificial muscle actuators, impossible in bulk metals or ceramics (Zhu et al., 2010).

Graphene films fabricated over large areas always contain defects, vacancies, or grain boundaries, wrinkles, or are misaligned in multi-layer stacks, all of which weaken the material by factors of 10 or even 100 compared to defect-free samples (Kim et al., 2010). On the same note, it is also not easy to distribute graphene in polymer or metal matrices and have it resist agglomeration; a bad interfacial contact would cause stress concentration and create a weak point to break even before the structures are fully loaded.

Certain scientists suggest hybrid reinforcement approaches- making the sheets of graphene more compatible with the use of particular matrices, or pairing the graphene with carbon nanotubes to link missing holes or make stronger the shedding of loads. Initial trials of comprising systems claim up to 30% gains in toughness over unmodified composites, although the challenges of scale-up remain: cost is increased by complex functionalization processes, and control of the nanoscale dispersion quality is not consistently gained to industrial quality (Xu et al., 2019; Smith et al., 2021).

ISSN 2959-6157

Although the mechanical strength and elasticity of graphene are much higher than those of strong competitors, commercialization hinges upon defect control and composite construction. When normal lab-scale sheets are an unusual scale of high performance or when they prove to be industrially manufacturable, it will determine whether graphene will actually redefine high-performance materials, or more often exist in niche, research-driven markets.

3.1.3 Cost and Availability

The cost of producing graphite is very high compared to the existing materials and is one of the many reasons that have already been cited as being a factor that prevents the growth of graphene in the market. Copper, silicon, and steel supply chains, in particular, have had decades of optimization and economies of scale, so refined copper prices are around 8000 per metric ton, whereas bulk silicon wafer prices have close to halved over the past decade to below 50 dollars per square inch. In comparison, monolayer graphene grown using chemical vapor deposition (CVD) could be sold at between 1,000 and 5,000 dollars per gram as of 2024, which is too expensive to be used in large applications (Markets and Markets, 2024).

Counter-argument: opponents say that the cost curve of graphene is following a similar trend to that of the early-day silicon photovoltaics, which initially enjoyed high manufacturing costs but saw these costs plummet by huge margins as the maturity of its application and production techniques were established. Other processes, e.g., liquid phase exfoliation, graphene oxide reduction, produce gram masses of material at a fraction of this unit cost and with far higher defect densities and property variability (Cheng et al., 2021).

Advocates point out that, with niche, high-value markets (aerospace composites, biomedicine), the high performance of graphene will allow charging a higher price and accelerate adoption in markets that are limited by high-performance material, rather than price per kilogram. Critics, however, respond that such niche victories mean little in moving the volumes required to realise the real economies of scale. With no high-throughput manufacture of high-quality, defect-free graphene, low-cost parity with existing materials is a distant goal. The current price of graphene and the raw immaturity of supply chains place graphene as a specialty material rather than a mass-market alternative. The potential of the current investments in roll-to-roll CVD, plasma enhanced deposition, and new approaches to exfoliation to fill the gap between premium niche markets and commoditized sectors will play an important role in what effect graphene will ultimately have in industry.

3.2 Future Prospects of Graphene Technologies

3.2.1 Graphene in Quantum Computing

The extremely high charge-carrier mobility and long coherence lengths of graphene have given rise to excitement that it can play a role in next-generation quantum devices. Proponents cite graphene-based Josephson junctions (in which superconducting contacts can bring Josephson tunnel effects to graphene) as potentially beneficial qubit platforms because of the potential to achieve high-frequency operation and be controllable using quantum Hall states that occur at high temperature (Allen et al., 2022). In addition, a bilayer of graphene under perpendicular electric fields exhibits a gate-tunable bandgap and topological insulating phases, indicating a path towards fault-tolerant qubits with reduced decoherence (Serlin et al., 2020).

Critics warn that the method has a long way to go, as “graphene qubits” have yet to leave the experimental research phase. Reproducible, low-defect graphene Josephson junctions on the wafer scale have been hindered by interface disorder and variations in contact transparency. Strong spin-based qubits are also difficult to realize, absent heavy atom proximity effects, which also add noise channels to the system, which is a challenge in making strong spin-coherence in graphene, which has a low intrinsic spin-orbit. Other authors propose further hybrid designs where the ability to couple graphene with high spin-orbit materials (e.g., transition metals dichalcogenides) can be exploited to achieve an effective control of the required spin-orbit coupling and, at the same time, maintain coherence.

Spin lifetimes in single-color prototypes are longer than those in silicon spin qubits, and it is not yet clear how such heterostructures might be incorporated into pipelines used to manufacture scalable quantum chips. The quantum potential of graphene cannot be disputed, yet the novel directions in the sphere of large-area production, interface design, and integration of heterostructures will be needed to achieve commercially viable quantum hardware. Its query is whether graphene becomes more than a laboratory toy, and whether it comes to be part of quantum computing will depend on whether these materials-science challenges can be overcome.

3.2.2 Graphene-enhanced Construction

The high mechanical strength and impermeability of graphene has already been used in building materials to offer possible performance and sustainability enhancement. A small percentage of graphene (0.03 -wpt -25) impregnated into cement can theoretically increase compressive strength by a quarter and decrease water permeability, which could allow thinning and strengthening of concrete elements with a proportional decrease in embodied carbon (Dimov et al., 2018). Its adherents believe that it might cause a radical decrease in carbon emissions of global infrastructure, which already amount to a % of emissions of cement production.

Nanoflakes in particle-rich matrices, which typically have high pH concentrations, are difficult to disperse uniformly; in case they are not dispersed well, reconstituted agglomerates become centralized crack starters instead of strengtheners. Even graphene at a discounted price of graphene oxide is a nontrivial cost premium on bulk materials, whose margins are very tight. In a few pilot projects, researchers have investigated in-line mixing approaches and surface-modified graphene to enhance compatibility with cement paste, with modest improvements in durability. However, the sceptics add that even when dispersion and cost problems are sorted out, the idea of graphene-enhanced concrete will still be limited to the niche luxury product but not to the building substance used as an everyday element.

3.2.3 Policy and Investment Trends

The material of graphene has drawn the attention of governments and industry groups across the globe. The European Commission has launched a single programme of this kind, the Graphene Flagship, a coordinated research initiative with a budget of more than 1 billion euros (Graphene Flagship, 2023). They involve more than 150 industry partnerships and have generated dozens of startups (Fitzsimons, 2023). Government multimillion-dollar projects have been spent on graphene in the U.S. by the National Nanotechnology Initiative and Department of Energy on energy storage, electronics, and biomedicine, and in China, this has culminated in the creation of dedicated industrial parks in Changzhou and Qingdao supporting an active R&D environment (Zhao et al., 2020).

With such a heavy investment, venture capital interest in graphene slackened in the years around 2015 as it proved difficult to achieve reproducible, large-scale announcements of breakthroughs, again rebounding in 2020 with interest in battery and 5G applications. Opponents complain that the piecemeal, application-specific funding threatens to keep graphene in the pilot-project status quo, instead of developing the stable norms, safety standards, and certification procedures that will be necessary before full industrial adoption is possible.

Policy analysts are proposing a two-track policy: continue funding at the basic-science level in an attempt to solve the material engineering bottlenecks, but favor special treatment of the early adopters in the high-value sectors (e.g., aerospace and defense and advanced electronics). As industrialization implies international characterization and safety tests standardization of graphene, uncertainty among the regulations can also be minimized and cross-border investments in the supply chain encouraged by other nations. The requisite groundwork is already in place in policy system research and investment but any prospective step to establish graphene as an industrial powerhouse will be determined by the concerted efforts of long-term research and development investments and the reality of commercialization and regulatory standardization.

4. Conclusion

Graphene is one of the hottest materials of the 21 st century that is known to exhibit excellent electrical characteristics, strengths and flexibilities, in addition to the thermal conductivity. As a result of an elaborate comparative study, this study has revealed that graphene is stronger than the traditional materials being used including silicon, copper and steel in various important areas or spheres and can, therefore, be used as an addition in next-generation technologies. High-speed electronics and next-generation batteries, biomedical developments, and sustainable building materials, among others, are possible applications of graphene and occur within the most vital areas of the world economy. Some serious impediments to the ubiquitous use of graphene technologies persist: graphene itself has no intrinsic bandgap, the manufacturing cost is prohibitively high, and such large-scale production schemes as the one being used are not available; experimentalists are worried about toxicity and chemical safety.

With these challenges, material science and nanofabrication and policy to enable the advancement are gradually becoming more efficient, and with one of the most promising directions being demonstrated through the EU Graphene Flagship or the national innovation zones in China, it is clear that this will be a good direction. The proliferating uses of quantum computing, intelligent infrastructure and clean energy offer hints that graphene may be the solution to the solutions to some of the most urgent technological and environmental issues over the next several decades. Probably, it is possible to overcome most of the existing restrictions during further multidisciplinary collaboration and intentional funding. Although graphene is not a panacea, one can consider it to be a platform material that can transform various industries radically.

5. Review

My project had the objective of describing the electrical, mechanical, and economic peculiarity of graphene, comparing its features with the already existing materials and

ISSN 2959-6157

critically evaluating the technological future of the substance both in the short and in the long term. This brought me to such a small focus at such an initial stage (to only look at 2D materials and to reduce the scale of materials to the scale of graphene) that I was then in a position to study so much on materials conductivity and strength, and cost regimes, and constructive comparative studies. Minor lack also exists in the sense that new developments so recent that new methods of roll-to-roll CVD are announced after April 2025 were not available to some extent because of delays in publication.

When looking back at my methodology, I would state that I initially did so with too broad a scope which delayed the focusing of further efforts and distilled future developments in the project. The shift to the graphene-only focus, however, alone, pushed the analysis into a more profound plane though, required a rewrite and a rewrite of Chapter 2 under time pressure. The advantage was that I could use Q1/Q2 journal articles that guaranteed quality of the sources at a cost of six to twelve months lag between publication and result in the latest state of the art conference results and patent advances were not well represented in the literature.

The project management, planning and research design was satisfactory but there was scope creep as per the project management, planning and research design that caused the schedule of the project to be delayed by an estimated one-week. The process of data collection/analysis succeeded, and comparative table and literature synthesis was prepared at the time. Two weeks lag in writing and revision stage was however partly occasioned by the high frequency of change in scope and the time wastage incurred in searching related studies. This last-minute pressure saw the final proofreading and formatting to be done only a day before the deadline episode which has necessitated the need to be more rigorous in making buffer plans.

In the future, I would go about doing the same tasks more carefully, at least in the initial phases of the project: during the first week, I would perform a fast and broad overview of the possible topics, and only then commit myself to a specific research question of a narrower focus. To avoid the destabilizing effect of late-breaking developments, I will also include a living document of emerging data, e.g., alerts log on conference feeds and patent watches. The number of journal researches and individual interviews with the experts or even webinars should be matched to address the interpretative discontinuity of the policy and market trends.

In the process, I have also been in a position to develop my skills in advanced search in databases (Web of Science, IEEE Xplore), evaluation of the credibility of the sources, and synthesis of information presented by interdisciplinary sources into a conceptual framework of arguments. The necessity to handle the requirements of the scientific writing style has sharpened my technical writing skills: I should employ a neutral language, correctly apply nomenclature, and not use cross-references. More importantly, and, I think, also, I have learnt how helpful agile project management techniques might have been in the research: the necessity to be sure that the scope is known beforehand, that one constantly monitors the newly appeared information and to introduce a feedback loop as iterative as possible in order to not only keep the project focus deep but also make it timely.

References

Ariga, K., (2022). Materials Nanoarchitectonics in a two-dimensional world within a nanoscale distance from the liquid phase. Nanoscale, 14(30), pp.10610-10629. https://doi.org/10.1039/D2NR02513B

Avsar, A., Ochoa, H., Guinea, F., Özyilmaz, B., Van Wees, B.J. and Vera-Marun, I.J., (2020). Colloquium: Spintronics in graphene and other two-dimensional materials. Reviews of Modern Physics, 92(2), p.021003. https://doi.org/10.1103/RevModPhys.92.021003

Dhall, S., Nigam, A., Harshavardhan, M., Mukherjee, A. and Srivastava, P., (2024). A comprehensive overview of methods involved in nanomaterial production and waste disposal from research labs and industries, and existing regulatory guidelines for handling engineered nanomaterials. Environmental Chemistry and Ecotoxicology. https://doi.org/10.1016/j.enceco.2024.06.002

Eivazzadeh-Keihan, R., Noruzi, E.B., Chidar, E., Jafari, M., Davoodi, F., Kashtiaray, A., Gorab, M.G., Hashemi, S.M., Javanshir, S., Cohan, R.A. and Maleki, A., (2022). Applications of carbon-based conductive nanomaterials in biosensors. Chemical Engineering Journal, 442, p.136183. https://doi.org/10.1016/j.cej.2022.136183

Iqbal, M.J., Kabeer, A., Abbas, Z., Siddiqui, H.A., Calina, D., Sharifi-Rad, J. and Cho, W.C., (2024). Interplay of oxidative stress, cellular communication, and signaling pathways in cancer. Cell Communication and Signaling, 22(1), p.7. https://doi.org/10.1186/s12964-023-01398-5

Jalali, M., Hassanzadeh, N., Alizadeh, R. and Langdon, T.G., (2024). Graphene-reinforced metal matrix composites produced by high-pressure torsion: a review. Journal of Materials Science, pp.1-29. https://doi.org/10.1007/s10853-024-10406-z

Kowsari, E., (2015). High-performance supercapacitors based on ionic liquids and a graphene nanostructure. In Ionic Liquids-Current State of the Art. IntechOpen. http://dx.doi.org/10.5772/59201

Krishnan, S.K., Nataraj, N., Meyyappan, M. and Pal, U., (2023). Graphene-based field-effect transistors in biosensing and

neural interfacing applications: recent advances and prospects. Analytical Chemistry, 95(5), pp.2590-2622. https://doi.org/10.1021/acs.analchem.2c03399
Li, Q., Lu, J., Gupta, P. and Qiu, M., (2019). Engineering optical absorption in graphene and other 2D materials: advances and applications. Advanced Optical Materials, 7(20), p.1900595. https://doi.org/10.1002/adom.201900595
Li, P., Wang, Z., Qi, Y., Cai, G., Zhao, Y., Ming, X., Lin, Z., Ma, W., Lin, J., Li, H. and Shen, K., (2024). Bidirectionally promoting assembly order for ultra-stiff and highly thermally conductive graphene fibers. Nature Communications, 15(1), p.409. https://doi.org/10.1038/s41467-024-44692-7
Liang, M., Yan, H., Wazir, N., Zhou, C., and Ma, Z., (2024). Two-Dimensional Semiconductors for State-of-the-Art Complementary Field-Effect Transistors and Integrated Circuits. Nanomaterials, 14(17), p.1408. https://doi.org/10.3390/nano14171408
MMR, (2025). Graphene Electronics Market – Global Industry Analysis And Forecast (2025-2032). https://www.maximizemarketresearch.com/market-report/global-graphene-electronics-market/29628/
Rahman, M.A., (2014). A review on semiconductors, including applications and temperature effects in semiconductors. American Scientific Research Journal for Engineering, Technology, and Sciences (ASRJETS), 7(1), pp.50-70. http://asrjetsjournal.org/
Saeed, M.A., Abdelkader, A., Alshammari, Y., Valles, C. and Alkandary, A., (2025). Graphene Applications in Composites, Energy, and Water Treatment. Macromolecular Materials and Engineering, p.2400316. https://doi.org/10.1002/mame.202400316
Sama, A., (2024). Introducing graphene-enhanced technologies to the regulated market to mitigate carbon emissions. Environmental Progress & Sustainable Energy, 43(1), p.e14338. https://doi.org/10.1002/ep.14338
Sengupta, J. and Hussain, C.M., (2022). Graphene-induced performance enhancement of batteries, touch screens, transparent Memory, and integrated circuits: A critical review on a decade of developments. Nanomaterials, 12(18), p.3146. https://doi.org/10.3390/nano12183146
Sonker, M., Bajpai, S., Khan, M.A., Yu, X., Tiwary, S.K. and Shreyash, N., (2021). Review of recent advances and their improvement in the effectiveness of hydrogel-based targeted drug delivery: A hope for treating cancer. ACS Applied Bio Materials, 4(12), pp.8080-8109. https://doi.org/10.1021/acsabm.1c00857
Szroeder, P., Banaszak-Piechowska, A. and Sahalianov, I., (2025). Tailoring Electrocatalytic Properties of sp2-Bonded Carbon Nanoforms Through Doping. Molecules, 30(6), p.1265. https://doi.org/10.3390/molecules30061265
Yang, K., Wang, J., Chen, X., Zhao, Q., Ghaffar, A. and Chen, B., (2018). Application of graphene-based materials in water purification: from the nanoscale to specific devices. Environmental Science: Nano, 5(6), pp.1264-1297. https://doi.org/10.1039/C8EN00194D
Yusaf, T., Mahamude, A.S.F., Farhana, K., Harun, W.S.W., Kadirgama, K., Ramasamy, D., Kamarulzaman, M.K., Subramonian, S., Hall, S. and Dhahad, H.A., (2022). A comprehensive review on graphene nanoparticles: Preparation, properties, and applications. Sustainability, 14(19), p.12336. https://doi.org/10.3390/su141912336
Zhang, X., Li, Y., Mu, W., Bai, W., Sun, X., Zhao, M., Zhang, Z., Shan, F. and Yang, Z., (2021). Advanced tape-exfoliated method for preparing large-area 2D monolayers: a review. 2D Materials, 8(3), p.032002. https://doi.org/10.1088/2053-1583/ac016f
Zhao, N., Song, M., Zhang, X., Xu, W. and Liu, X., (2024). Nanodiamond coating in energy and engineering fields: synthesis methods, characteristics, and applications. Small, 20(36), p.2401292. https://doi.org/10.1002/smll.202401292